

AM POWDERS





Refractory Alloy Powders
for Additive Manufacturing



MATCHING THE MATERIAL PROPERTIES WITH THE AM METHODS NEEDED TO SERVE THE MARKETS

Based on 100 years of experience in manufacturing and development of refractory metals, Elmet Technologies has powder and wire feedstock with tailored properties perfectly suited for Additive Manufacturing (AM). The company's core competencies of W, Mo, Ta, and Nb, in pure and alloyed forms, ensure materials with the highest quality and performance for our customers. With our unique understanding of refractory metals, we help our customers to select the correct material and AM method to best meet the requirements of their application.

As an integrated player, we use our feedstock materials and turn them into innovative finished products using the best suited additive manufacturing methods.



TAILORED SOLUTIONS FOR YOUR AM APPROACH

Elmet Technologies' AM powders are specifically designed to meet the demanding requirements of additive manufacturing technologies, with properties that have proven success

TYPICAL PROPERTIES OF AM POWDERS FOR PBF-L

PROPERTY	UNIT	NIObIUM	MOLYBDENUM	TANTALUM	TUNGSTEN
Purity	%	>99.95	>99.95	>99.95	>99.95
Mean Particle Size D50	µm	25-35	25-35	25-35	25-35
D10/D90*	µm	15/45	15/45	15/45	15/45
Bulk Density	g/cc	4	5	8	10
Hall Flow	s/50g	14-16	8-10	5-9	5-8
Oxygen	ppm	1500	400	300	250

*Other particle size ranges are available for AM methods such as DED or PBF-EB

Elmet Technologies' innovative powder and wire manufacturing technology coupled with our vertically integrated supply chain and metallurgical expertise ensures the highest quality materials for demanding applications and environments. Our advanced technological processes enable us to customize our refractory metal feedstock to precise requirements achieving outstanding material properties and optimum performance for additive manufacturing.

OUR POWDER ADVANTAGE

- > High purity
- > High bulk density
- > Spherical or flake powder morphology
- > Exceptional flowability
- > Low oxygen
- > PSD optimized for specific printing methods
- > Volumes from laboratory to production scale
- > 100 years of refractory metal experience
- > R&D capabilities to develop custom alloys

OUR CUSTOMIZED PORTFOLIO

- > High bulk density
- > Spherical or flake powder morphology
- > Exceptional flowability
- > Low oxygen

We continuously develop new materials and methods and are ready to support your unique requests



ELMET TECHNOLOGIES

1560 Lisbon Street • Lewiston, Maine 04240

P +1.207.333.6100

sales@elmettech.com

www.elmettechnologies.com

The conditions of your use and application of Elmet Technologies products, technical assistance, and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, is your responsibility. Therefore, you are encouraged to test our products and review any technical assistance and/or information you may receive from Elmet Technologies with your own resources, and determine to your own satisfaction whether Elmet Technologies products are suitable for your intended uses and applications. This application-specific analysis should include at minimum testing to determine suitability for the intended use from a technical as well as health, safety, and environmental standpoint. Any technical assistance and/or information provided by Elmet Technologies is given without any express or implied warranty or guarantee. You agree and understand and hereby expressly release Elmet Technologies from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and/or information, except as may be contained otherwise in a written agreement between you and Elmet Technologies. Any statement or recommendation not contained herein or in a written agreement between you and Elmet Technologies is unauthorized and shall not bind Elmet Technologies. Nothing herein shall be construed as a recommendation to use any Elmet Technologies products in a manner violative of the intellectual property rights of any third party. No license is implied or granted under or to Elmet Technologies intellectual property. All product deliveries are based on the then current product specification and Elmet Technologies' Conditions of Sale. IN NO EVENT WILL ELMET TECHNOLOGIES BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.