

MOLYBDENUM ARC-CAST PRODUCTS

MOLYBDENUM ALLOY AB-30W

Arc-Cast Bar


This specification covers wrought bar of carbon-deoxidized molybdenum 30 % tungsten alloy produced from ingots consolidated by the consumable electrode vacuum-arc-casting process.

CHEMICAL CHARACTERISTICS¹

(Mass fraction in % [cg/g]; ppm [μ g/g])

The chemical composition of the billet used for producing the wrought bar shall conform to the following limits:

Mo (By Difference)	min.	99.2 %
Tungsten	27.0 -	33.0 %
Ni	max.	0.002 %
*N	max.	0.002 %
*O	max.	0.0025 %
Fe	max.	0.008 %
Si	max.	0.008%
C	max.	0.030 %



ARC-CAST PRODUCTS

*Unless method of analysis is agreed upon, deviations from these limits alone shall not be cause for rejection.

STRUCTURE

Bar will be supplied in a stress-relieved condition. Material can be supplied in the recrystallized condition upon request.

¹ Information on testing methods on request.

MECHANICAL PROPERTIES

The hardness of stress-relieved material will be determined to conform to the following (measured at mid-radius location):

Diameter		Hardness	DPH (10 kg)
Inches	mm	Minimum	Maximum
Over 1/8 to 7/8	3.2 - 22.2	240	300
Over 7/8 to 1 1/8	22.2 - 28.6	235	300
Over 1 1/8 to 1 7/8	28.6 - 34.9	230	290
Over 1 7/8 to 2 7/8	34.9 - 73.0	230	290

Tensile properties can be supplied, at additional cost, if requested at time of order.

DIMENSIONAL TOLERANCES

Diameter		Diameter Variation		Out-of-Round	
Inches	mm	Inches	mm	Inches	mm
1/8 to 9/32	3.2 - 7.1	+0.002 -0.002	+0.05-0.05	0.004	0.10
Over 9/32 to 13/32	7.1 - 10.3	+0.003 -0.003	+0.07-0.07	0.006	0.15
Over 13/32 to 5/8	10.3 - 15.9	+0.010 -0.005	+0.25-0.13	0.012	0.30
Over 5/8 to 7/8	15.9 - 22.2	+0.015 -0.005	+0.38-0.13	0.015	0.38
Over 7/8 to 1	22.2 - 25.4	+0.020 -0.005	+0.51-0.13	0.015	0.38
Over 1 to 1 3/8	25.4 - 34.9	+0.020 -0.010	+0.51-0.25	0.018	0.46
Over 1 3/8 to 1 1/2	34.9 - 38.1	+0.020 -0.015	+0.51-0.38	0.020	0.51
Over 1 1/2 to 1 5/8	38.1 - 41.3	+0.025 -0.015	+0.64-0.38	0.020	0.51
Over 1 5/8 to 2	41.3 - 50.8	+0.030 -0.020	+0.76-0.51	0.025	0.64
Over 2 to 2 1/2	50.8 - 63.5	+0.032 -0.032	+0.81-0.81	0.025	0.64
Over 2 1/2 to 3 1/2	63.5 - 88.9	+0.032 -0.032	+0.81-0.81	0.027	0.69

Special finished bars can be supplied with a tolerance of ± 0.002 inch for 2 inches diameter or smaller sizes, and ± 0.003 inch for larger size bars.

Maximum variation from straightness will be 0.050 inch per foot.

Maximum variation in cut length will be $+ \frac{1}{4}$ inch, -0.

SURFACE CONDITION

Bars will be supplied with chemically or mechanically cleaned surfaces. Minor surface imperfections, revealed by dye penetrant inspection, may be removed by conditioning, provided such removal does not reduce dimensions below specified tolerance limits. Special finished bars will be supplied with a surface finish of 90 RMS or better.

IDENTIFICATION

Bar will be identified with an appropriate lot number. Each shipping container will be marked with the name of the customer and the purchase order number.

HAZARDS IDENTIFICATION IN ADVERTISING (DIRECTIVE 67/548/EEC ARTICLE 26, DIRECTIVE 1999/45/EC ARTICLE 13 AND REGULATION (EC) NO 1272/2008 ARTICLE 48)

REPORTS

A product certification report that details pertinent chemical, mechanical, structural and physical integrity features will be provided.

REJECTION

Elmet Technologies must receive written notification of rejected material with the reason for rejection. The right is reserved to inspect rejected material at customer plant for claim validation. The material may be returned only after proper authorization.



ELMET TECHNOLOGIES

1560 Lisbon Street • Lewiston, Maine 04240

P +1.207.333.6100

sales@elmettech.com

www.elmettechnologies.com

The conditions of your use and application of Elmet Technologies products, technical assistance, and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, is your responsibility. Therefore, you are encouraged to test our products and review any technical assistance and/or information you may receive from Elmet Technologies with your own resources, and determine to your own satisfaction whether Elmet Technologies products are suitable for your intended uses and applications. This application-specific analysis should include at minimum testing to determine suitability for the intended use from a technical as well as health, safety, and environmental standpoint. Any technical assistance and/or information provided by Elmet Technologies is given without any express or implied warranty or guarantee. You agree and understand and hereby expressly release Elmet Technologies from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and/or information, except as may be contained otherwise in a written agreement between you and Elmet Technologies. Any statement or recommendation not contained herein or in a written agreement between you and Elmet Technologies is unauthorized and shall not bind Elmet Technologies. Nothing herein shall be construed as a recommendation to use any Elmet Technologies products in a manner violative of the intellectual property rights of any third party. No license is implied or granted under or to Elmet Technologies intellectual property. All product deliveries are based on the then current product specification and Elmet Technologies' Conditions of Sale. IN NO EVENT WILL ELMET TECHNOLOGIES BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.