

ULTRA 76 PLUS ALLOY (Ta 2.5%W)

Benefits Significantly improved corrosion resistance in HCl and H₂SO₄ acids.
Minimized hydrogen embrittlement rates compared to standard NRC®76
Up to 100 times lower in HCl acid
Up to 10 times lower in H₂SO₄ acid
Eliminates the need for a separate Pt application step to protect against H embrittlement.
Maintains all the excellent mechanical properties of NRC®76.
Potential for increased operating temperatures in both HCl and H₂SO₄.

Applications High strength alloy for corrosion applications in heat transfer equipment, vessels, piping, etc., and all applications where tantalum's physical properties are desired at a higher strength level than pure tantalum, and better corrosion resistance in HCl and H₂SO₄ acids.

Forms Available Foil: 0.001" to 0.006" thick by widths up to 12" wide. Sheet: 0.006" to 0.1875" thick by widths up to 40" wide. Plate 0.1875" to 1" thick in common widths. Welded Tubing .015" to .035" wall x 1/2" to 2" diameter. Also, rod, plate, wire, bar and customer specified specialty sizes of all materials.

Chemical Characteristics¹⁾ (Mass fraction in % [cg/g]; ppm [µg/g])

Element	ppm (max)	Element	ppm (max)
C	50	Ti	40
O	100	Ni	50
N	50	Mo	200
H	10	Si	25
Nb	0.1 % (1000)	W	2.0 - 3.5 wt %
Fe	50	PGM*	1000 - 2000
Ta	balance		

*Platinum Group Metals

Mechanical Properties (Design minimum)

Temp °F	Yield Strength 0.2% offset KSI	Tensile Strength (KSI)	Elongation % inch
70	35.5	50	20
210	30.5	48	15
390	27.4	42	10
480	25.5	40	10

Metallurgical Characteristics

Material is single-phase tantalum with tungsten and platinum group metals in solid solution.
Stress relieve at 2000°F
Re-crystallize at 2400°F

1) Information on testing methods on request.

Number PD-7049
 Issue 1-05/05/2021

Physical Properties

Density		0.602	Lb/in ³
Melting Point		2996	°C
Coefficient of Expansion (20° - 500° C)		3.6 X 10 ⁻⁶	°F ⁻¹
Specific Heat (at 100° C)		0.0336	BTU/Lb°F
Thermal Conductivity (20° – 100°)		32	BTU/Hr-Ft °F
Electrical Resistivity (0° – 100°)		14.7	Microhm-cm
Thermal Neutron Absorption Cross Section		21.3	Barns/atom
Typical Ultimate Tensile Strength at 20° C		45 - 55	KPSI
Typical Yield Strength at 20° C		35 - 45	KPSI
Modulus of Elasticity		27 X 10 ⁶	PSI
Hardness as Annealed (Typical)	Vickers	115 - 160	
	Rockwell B	50 - 80	

Main Products

- Bayonet Heaters** - Single and multi-tube types for use in steam heating in corrosive atmospheres.
- Heat Exchangers, Condensers and Coils**
- Thermocouple Protection Sheaths** Loose lined or machined from solid.
- Pumps, Bodies or Cases, Shafts and Impellers** - For corrosive chemical solutions.
- Paddle Stirrers and Agitators** - Solid or covered (loose-lined)
- Distillation Columns, Boilers and Condensers**
- Tantalum Clad Dip Pipes, Heaters and Chemical Plant Equipment**
- Repairs Kits** - For tanks, vats and other glass-lined containers
- Crucibles** - In standard and special shapes and sizes
- Furnaces and Furnace Parts** - For use at temperatures up to 2500°F in controlled atmospheres.

Hazards identification in Advertising (Directive 67/548/EEC Article 26, Directive 1999/45/EC Article 13 and REGULATION (EC) No 1272/2008 Article 48)
 Metal powder, flammable, n.o.s.

H.C. Starck Inc.
 45 Industrial Place
 Newton, MA 02461-1951 / USA
 Phone +1 (617) 630-5800, Fax +1 (617) 630-5879

info@hcstarcksolutions.com

www.hcstarcksolutions.com

The conditions of your use and application of H.C. Starck products, technical assistance, and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, is your responsibility. Therefore, you are encouraged to test our products and review any technical assistance and/or information you may receive from H.C. Starck with your own resources, and determine to your own satisfaction whether H.C. Starck products are suitable for your intended uses and applications. This application-specific analysis should include at minimum testing to determine suitability for the intended use from a technical as well as health, safety, and environmental standpoint. Any technical assistance and/or information provided by H.C. Starck is given without any express or implied warranty or guarantee. You agree and understand and hereby expressly release H.C. Starck from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and/or information, except as may be contained otherwise in a written agreement between you and H.C. Starck. Any statement or recommendation not contained herein or in a written agreement between you and H.C. Starck is unauthorized and shall not bind H.C. Starck. Nothing herein shall be construed as a recommendation to use any H.C. Starck products in a manner violative of the intellectual property rights of any third party. No license is implied or granted under or to H.C. Starck intellectual property. All product deliveries are based on the then current product specification and H.C. Starck's Conditions of Sale. IN NO EVENT WILL H.C. STARCK BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Number PD-7049
 Issue 1-05/05/2021

In hydrochloric acid applications using higher temperatures and concentrations, Ultra 76 Plus improves corrosion resistance, but more importantly, hydrogen embrittlement is minimized, as hydrogen pickup is reduced by two magnitudes over standard NRC[®]76 material. Similar results are seen in sulphuric acid applications. Use of Ultra 76 Plus will help extend equipment life, reduce downtime and allow operation in more demanding environments compared to alternative materials.

