

QR3A Capacitor Grade Tantalum

Number PD-7060  
 Issue 1-05/05/2021

## QR3A Capacitor Grade Tantalum

**Description of Product** This product data sheet covers the requirements for the production, handling, and testing of QR3A High Voltage, Capacitor Grade, Tantalum Powder manufactured by H.C. Starck, Newton, MA.

### Physical Characteristics

	Min.	Max.
Fisher Subsieve Sizer FAPD [micron]	4.5	6.5
Scott Bulk Density SBD [g/in <sup>3</sup> ]	50.0	60.0
F.S.S.		
	% +60 mesh	N/A
	% -325 mesh	40.0
		65.0

### Chemical Characteristics

(ppm)

	Max.
Boron [B]	20
Calcium [Ca]	2
Carbon [C]	25
Copper [Cu]	5
Molybdenum [Mo]	5
Niobium [Nb]	10
Nitrogen [N]	80
Oxygen [O]	2300
Potassium [K]	10
Silicon [Si]	20
Sodium [Na]	1
Sulfur [S]	10
Titanium [Ti]	5
Tungsten [W]	40
Sum of: [Ni], [Fe], [Cr]	25

### Electrical Characteristics

#### Electrical Test 1

Sinter Temp./Time	1600 C
Voltage	150
% Wild Anodes	0
CV/g (normalized) [ufV/g]	6000 min. 7000 max.
VBD [V]	180 min.

Number PD-7060  
Issue 1-05/05/2021

**Electrical Test 2**

Sinter Temp./Time	1800 C	
Voltage	200	
% Wild Anodes		0
CV/g (normalized) [ufV/g]	4400 min.	5000 max.
VBD [V]	240 min.	

**Hazards identification in Advertising (Directive 67/548/EEC Article 26 and Directive 1999/45/EC Article 13)**

Metal powder, flammable, n.o.s.

**Packaging**

The H.C. Starck Solutions convention has been to package this material in 1 liter Nalgene polyethylene bottles at a maximum weight of 5kg/bottle.

**Rejection**

H.C. Starck Solutions must receive written notification of rejected material with the reason for rejection. The right is reserved to inspect rejected material at customer plant for claim validation. The material may be returned only after proper authorization.

H.C. Starck Inc.  
45 Industrial Place  
Newton, MA 02461-1951 / USA  
Phone +1 (617) 630-5800, Fax +1 (617) 630-5879