

MOLYBDENUM-COPPER COMPOSITE MATERIALS

Product description:

Molybdenum-copper composite materials are produced by copper infiltration of porous sintered molybdenum. They are available with different copper contents. A thermal conductivity over 200 W/m*K is producible.

Range of application:

Switching contacts for high-voltage and medium-voltage, heat sinks for passive thermal management (rolled sheets), electrodes for erosive processing.

Typical properties:

Material	MoCu	65/35	70/30	80/20	Material
Molybdenum content	%	65 ± 3	70 ± 3	80 ± 3	Molybdenum content
Copper content	%	35 ± 3	30 ± 3	20 ± 3	Copper content
Density	g/cm ³	9,72 ± 0,04	9,78 ± 0,04	9,92 ± 0,05	Density
Hardness	HB2,5/62,5	120 - 160	130 - 170	135 - 175	Hardness
Median coefficient of linear thermal expansion (20 – 100 °C)	10 ⁻⁶ /K	8,6	8,2	6,3	Median coefficient of linear thermal expansion (20 – 100 °C)
(20 – 300 °C)	10 ⁻⁶ /K	9,2	8,6	6,4	(20 – 300 °C)
(20 – 450 °C)	10 ⁻⁶ /K	9,6	8,8	6,6	(20 – 450 °C)
Young' s modulus (guide value)	GPa	200	210	220	Young' s modulus (guide value)
Ultimate tensile strength Typical value (round bar) Typical value (sheet)	MPa	280 370 650	290 420 720	300 470 750	Ultimate tensile strength Typical value (round bar) Typical value (sheet)
Electrical conductivity	%IACS MS/m	≥ 47 ≥ 27	≥ 45 ≥ 26	≥ 35 ≥ 20	Electrical conductivity
Specific electrical resistance	Ω*mm ² /m	≤ 0,040	≤ 0,038	≤ 0,042	Specific electrical resistance
Thermal conductivity	W/m*K	≥ 200	≥ 190	≥ 170	Thermal conductivity

Nummer PD-7101
Stand 1-2020-11-19

Delivery form:

The products may be delivered as semi-finished products (round bars or sheets) for further machining by the customer or according to customer drawing as finished products.

H.C. Starck Hermsdorf GmbH
Robert-Friese-Strasse 4
07629 Hermsdorf
Phone +49 36601 922-101, Fax +49 36601 922-111

info@hcstarcksolutions.com

www.hcstarcksolutions.com

The conditions of your use and application of our products, technical assistance and information (whether verbal, written by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such tests do not necessarily need to be performed by H.C. Starck. All information is without warranty or guarantee. It formally must be understood and agreed that the customer assumes and hereby expressly releases H.C. Starck from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind H.C. Starck. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent. In case of order please refer to issue number of this product data sheet. All deliveries are based on the latest issue of the product data sheet and the latest version of our General Conditions of Sales and Delivery.