



High Performance Metal Solutions

# Tungsten Alloys

Radiation Shielding and High Density Materials  
for Well Logging Instrumentation

H.C.Starck 

High Performance Metal Solutions




# Fabricated Tungsten Alloys Enhance Oil and Gas Drilling

H.C. Starck Solutions' high tech materials, technologies and development expertise are producing value added solutions for the high performance demands of the oil and gas drilling industry.


As one of the world's leading producers of refractory metals such as tantalum, niobium, molybdenum and tungsten, H.C. Starck Solutions' tungsten alloys has become an essential material for a wide variety of applications including balance weights, radiation protection, vibration absorbers, heat transfer and drilling bars. It has the highest melting point of any metal and its high density is equaled only by gold, platinum, and a few other rare and expensive metals.

## Protecting Data Logging Instrumentation

The radiation shielding properties of tungsten alloy materials are excellent for use in fabricating products to enclose data logging instrumentation and isotopes, essential to locating oil and gas deposits. By shielding the instrumentation and personnel from radiation it dramatically improves the performance of the data logging.



H.C. Starck Solutions' tungsten alloy products enhance real-time data logging while optimizing the drilling performance, improve rates of drilling stability and reduce the cost and time of searching for these vital resources. In addition, H.C. Starck Solutions' tungsten alloy products shield the gamma camera and sensors from the grueling work of drilling through the earth's layers.




## Sinker Bars

The high density of tungsten alloys, which is critical to the radiation shielding, are also extremely beneficial for sinker bar applications. These high density weights or series of weights are attached to the down hole logging tool assemblies in order to add the extra weight to help the tool properly descend through the heavy borehole fluids.

## Mechanical Properties


Mechanical properties of tensile strength, ductility and hardness plus other elemental metals, create a family of tungsten alloy materials that have found wide acceptance where a concentrated mass is required in a limited space. Tungsten alloys guarantee the strength and stability needed for the tough oil and gas drilling process.



Tungsten alloys are economically fabricated by powder metallurgy techniques and routinely machined by conventional methods. H.C. Starck Solutions' tungsten alloy products are delivered both as a semi finished product for further processing by the customer or in accordance with the customer's drawing as a finished machined component. To meet the specific applications of our customers, we recommend the delivery of the finished machined product.

## Tungsten's Radiation Absorption Efficiency

The absorption of x-ray and gamma radiation is in direct proportion to the density of the shielding material. Tungsten high density composites are more than 1.5 times as effective as lead and provide extremely efficient protection, particularly where space is limited.



## Typical Properties

K1700 to K1850 materials provide a solution in a wide range of applications requiring concentrated weight or density in a limited space. These lead-free parts meet legal requirements and recommendations to protect the environment.

Alloy Designation		K1700	K1701	K1750	K1800	K1801	K1850
Tungsten content	(%)	90	90	92.5	95	95	97
Density	(g/cm <sup>3</sup> )	17	17	17.5	18	18	18.5
	(lb/in <sup>3</sup> )	0.61	0.61	0.63	0.65	0.65	0.67
Hardness	(Rc)	23	22	24	25	24	26
Ultimate Tensile Strength	(psi)	125,000	110,000	125,000	125,000	110,000	120,000
	(N/mm <sup>2</sup> )	860	760	860	860	760	830
Yield Strength	(psi)	85,000	80,000	90,000	90,000	85,000	95,000
	(N/mm <sup>2</sup> )	590	550	620	620	590	660
Elongation	(% in 1 inch)	12	4	10	8	2	6
Modulus of Elasticity	(psi × 10 <sup>6</sup> )	45	40	46	48	45	50
	(kN/mm <sup>2</sup> )	310	280	320	330	310	345
Magnetic Properties		slight	none	slight	slight	none	slight
Magnetic Permeability		> 1.05	< 1.05	> 1.05	> 1.05	< 1.05	> 1.05
Thermal Expansion Coefficient	(×10 <sup>-6</sup> /°C)(200 °C – 5000 °C)	5.1	5.4	4.9	4.8	5.0	4.8
Thermal Conductivity	(cgs)	0.20	0.23	0.24	0.27	0.32	0.26
Electrical Conductivity	(% IACS)	11	14	12	15	16	16
AMS-T-21014	class	1	1	2	3	3	4
ASTM B777	class	1	1	2	3	3	4

Tungsten alloys exceed requirements of the following specifications: AMS-T-21014, ASTM B777 AND AMS 7725. H.C. Starck Solutions' tungsten alloy materials can be designed and fabricated to the customer's specifications.

## USA

### **H.C. Starck Solutions Euclid, LLC**

21801 Tungsten Road  
Euclid, OH 44117-1117 USA  
T +1 216 692 3990  
F +1 216 692 0029

### **H.C. Starck Solutions**

199 Wells Ave #107  
Newton, MA 02459 USA  
T +1 617 630 5800  
F +1 617 630 5879

### **H.C. Starck Solutions Coldwater, LLC**

460 Jay Street  
Coldwater, MI 49036 USA  
T +1 517 279 9511  
F +1 517 269 9512

## Japan

### **H.C. Starck Fabricated Products GK**

3F Shiodome Building,  
1-2-20 Kaigan,  
Minato-ku, Tokyo  
105-0022 JAPAN  
T +81-3-6721-8177  
F +81-3-6733-8896

DPAP 03/2020

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis at least must include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by H.C. Starck Solutions. All information is given without warranty or guarantee. It is expressly understood and agreed that the customer assumes and hereby expressly releases H.C. Starck Solutions from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind H.C. Starck Solutions. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent. Properties of the products referred to herein shall as general rule not be classed as information on the properties of the item for sale. In case of order please refer to issue number of the respective product data sheet. All deliveries are based on the latest issue of the product data sheet and the latest version of our General Conditions of Sale and Delivery.

The values in this publication are typical values and do not constitute a specification.

[info@hcstarcksolutions.com](mailto:info@hcstarcksolutions.com)  
[www.hcstarcksolutions.com](http://www.hcstarcksolutions.com)

**H.C. Starck**   
**High Performance Metal Solutions**