



TUNGSTEN HIGH DENSITY ALLOYS

TUNGSTEN HIGH DENSITY ALLOYS

Tungsten-based alloyed materials are outstanding due to their high density and exceptional mechanical properties characterized by ductility and hardness and whose high density is equaled only by gold, platinum, and a few other rare and expensive metals.

Tungsten alloys are exceptional for applications were maximum concentrated weight is required in the smallest possible space. The addition of chemical elements such as nickel, copper, and iron, creates a family of tungsten alloys with extremely useful properties for machining. These alloys are economically fabricated by powder metallurgy techniques and are routinely machined by conventional methods.

Tungsten alloys can be delivered both as semi-finished product for further processing by the customer or in accordance with the drawing as finished machined component. To meet the specific application of our customers we recommend the delivery of the finished machined product.

Our K1700 to K1850 materials provide a solution in a wide range of applications requiring concentrated weight or density in a limited space. These lead-free parts meet legal requirements and recommendations to protect the environment. Twice as heavy as steel and more than 50% heavier than lead, tungsten alloys have become an essential material for a wide variety of applications in aerospace, defense, medical, and oil and gas exploration.

RANGE OF APPLICATION

Balance weights, radiation protection, vibration absorbers, heat transfer, drilling bars. The mechanical characteristics have to guarantee the stability and strength in any application case.

The absorption of x-ray and gamma radiation is in direct proportion to the density of the shielding material. Tungsten high density composites are more than 1,5 times as effective as lead and provide extremely efficient protection, particularly where space is limited.

STANDARDS

Exceeds requirements of the following specifications: MIL-T-21014, ASTM B777 and AMS 7725

TYPICAL PROPERTIES OF TUNGSTEN HIGH DENITY ALLOYS

Characteristics		Material					
Alloy Designation	mm	K1700	K1701	K1750	K1800	K1801	K1850
Tungsten content (%)	(%)	90	90	92.5	95	95	97
Density	(g/cm3)	17	17	17.5	18	18	18.5
	(lb/in3)	0.61	0.61	0.63	0.65	0.65	0.67
Hardness	(Rc)	23	22	24	25	24	26
Ultimate Tensile Strength	(psi)	125,000	110,000	125,000	125,000	110,000	120,000
	(N/mm2)	860	760	860	860	760	830
Yield Strength	(psi)	85,000	80,000	90,000	90,000	85,000	95,000
	(N/mm2)	590	550	620	620	590	660
Elongation	(%)	12	4	10	8	2	6
Modulus of Elasticity	(psi x 106)	45	40	46	48	45	50
	(kN/mm2)	310	280	320	330	310	345
Magnetic Properties		slight	none	slight	slight	none	slight
Magnetic Permeability	(µ)	>1.05	<1.05	>1.05	>1.05	<1.05	>1.05
Thermal Expansion Coefficient	(x10-6/K)(20°C-500°C)	5.1	5.4	4.9	4.8	5.0	4.8
Thermal Conductivity	(cgs)	.20	.23	.24	.27	.32	.26
Electrical Conductivity	(% IACS)	11	14	12	15	16	16
MIL-T-21014(D)	class	1	1	2	3	3	4

MECHANICAL PROPERTIES

Tensile properties can be supplied on request when Purchase Order is placed.

CHEMICAL PROPERTIES

Chemical properties can be supplied on request when Purchase Order is placed.

HAZARDS IDENTIFICATION IN ADVERTISING (REGULATION (EC) NO 1272/2008 ARTICLE 48)

None.

DELIVERY FORM

Tungsten alloy products can be delivered both as semi-finished products for further processing by the customer or as a finished product in accordance with drawing specifications. These lead-free products meet legal requirements and recommendations to protect the environment.

REJECTION

Elmet Technologies must receive written notification of rejected material with the resaon for rejection. The right is reserved to inspect rejected material at customer plant for claim validation. The material may be returned only after proper authorization.



ELMET TECHNOLOGIES

1560 Lisbon Street • Lewiston, Maine 04240

P+1.207.333.6100

sales@elmettech.com www.elmettechnologies.com The conditions of your use and application of Elmet Technologies products, technical assistance, and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, is your responsibility. Therefore, you are encouraged to test our products and review any technical assistance and/or information you may receive from Elmet Technologies with your own resources, and determine to your own satisfaction whether Elmet Technologies products are suitable for your intended uses and applications. This application-specific analysis should include at minimum testing to determine suitability for the intended use from a technical as well as health, safety, and environmental standpoint. Any technical assistance and/or information provided by Elmet Technologies is given without any express or implied warranty or guarantee. You agree and understand and hereby expressly release Elmet Technologies from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and/or information, except as may be contained otherwise in a written agreement between you and Elmet Technologies. Any statement or recommendation not contained herein or in a written agreement between you and Elmet Technologies is unauthorized and shall not bind Elmet Technologies. Nothing herein shall be construed as a recommendation to use any Elmet Technologies products in a manner violative of the intellectual property rights of any third party. No license is implied or granted under or to Elmet Technologies intellectual property. All product deliveries are based on the then current product specification and Elmet Technologies' Conditions of Sale. IN NO EVENT WILL ELMET TECHNOLOGIES BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.